

Material	Norms			Serviceability			Optional			
	Weight [g/m ²] DIN EN 1227	Antistatic DIN EN 1149-5	Oeko-Tex® Standard 100	Long-Term Temperature Resistance	Washing Resistance DIN EN ISO 6330	Abrasion Resistance [turns] DIN EN ISO 12947-2, 12 kPa	Standard FC-finishing DIN EN ISO 4920 / DIN EN ISO 14419	PowerShell (permanent FC-finishing) DIN EN ISO 4920 / DIN EN ISO 14419	Standard hydrophilic-finishing	Soft & Dry (permanent hydrophilic finishing)
Nomex® Comfort 93% Meta-Aramide/5% Para-Aramide/2% Antistatic	150	X	X	250 °C	6N ^h , F [60 °C]	≥ 30.000	X		X	X
	170	X	X	250 °C	6N ^h , F [60 °C]	≥ 30.000	X	X	X	X
	180	X	X	250 °C	6N ^h , F [60 °C]	≥ 30.000	X	X	X	X
	190	X	X	250 °C	6N ^h , F [60 °C]	≥ 30.000	X	X	X	X
	220	X	X	250 °C	6N ^h , F [60 °C]	≥ 30.000	X	X	X	X
	265	X	X	250 °C	6N ^h , F [60 °C]	≥ 40.000	X	X	X	X